

PP 底材附着增进剂



产品介绍

Hardlen 16-LP 为氯化 PP 树脂，广泛的应用于 PP 薄膜及塑料的粘合剂，也可作为油墨与涂料的粘结料，而不须 PP 表面经过放电、火焰等表面处理。

产品特征

组成	氯化 PP
外观	微黄色颗粒
软化点	约 89°C

应用领域

OPP 膜与油墨的粘合。

主要特性

- 由于 Hardlen 16-LP 对聚丙烯具有强大的粘合力，故不须经电晕放电、火焰、氧化剂等表面处理，就可作为聚丙烯薄膜及塑料制成品上油墨的的粘结料。
- Hardlen 16-LP 成膜后的薄膜透明而强韧，具有良好的耐药品性。

* 关于氯化聚烯烃的使用方法，本公司备有详细技术资料，欢迎联系索取。

使用方法

以甲苯溶解成约 20 - 30% 后直接使用或加入油墨中。

添加量

- 底涂使用，溶剂甲苯或二甲苯稀释 5 - 10 倍。
- 添加在树脂中，对树脂全量添加 5 - 15%，请考虑相容性。

操作与安全

小心操作，避免接触皮肤与眼睛，其它资料请参考物质安全资料表。

储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存条件为 0°C 至 40°C。

包装

净重：20 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B01 Jan-10

有效期

Hardlen 16-LP 自生产日起, 保质期限为 24 个月。

品质保证

本公司自 1992 年起获得 ISO 9001／9002 质量体系认证，确保所有操作符合标准规定。

海名斯特殊化学，亚洲

Head Office

上海市松江工业区联阳路 99 号
邮编 201613
99, Lianyang Road, Songjiang
Industrial Zone, Shanghai,
China 201613
Tel.: +86 21 57740348
Fax.: +86 21 57743563

Taiwan

新竹县湖口乡新竹工业区光复北路
92 号
92, Kuang-Fu North Road, Hsinchu
Industrial Park, Hukou,
Hsinchu, Taiwan
Tel.: +886 3 5984035
Fax.: +886 3 5983301

Malaysia

Lot PT 55, 64 & 65,
Jalan Hulu Tinggi 26/6, Seksyen 26,
40400 Shah Alam Selangor Darul
Ehsan, Malaysia
Tel.: +603 5191 9979
Fax.: +603 5191 6811

Japan

15-14 Minamimiseba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6210
Fax.: +81 6 6267 6213