

## 流平剂

### 产品介绍

Levaslip 468 为改性聚硅氧烷流平剂, 提供流平与平滑的功效。

### 产品特征

|      |                     |
|------|---------------------|
| 组成   | 改性聚硅氧烷              |
| 外观   | 澄清至混浊液体             |
| 不挥发份 | >94.5%              |
| 比重   | 1.00 - 1.03         |
| 粘度   | 175 - 390 cP (25°C) |

### 应用领域

- 溶剂型涂料
- 无溶剂型涂料
- 紫外光固化涂料
- 水性涂料
- 紫外光柔性版丝网油墨
- 水性油墨

### 主要特性

- 具优异的平滑性, 可显着增加涂膜滑感及抗划伤性。
- 效率高, 在低添加量下, 就有优异效果。
- 增进涂膜流动与流平, 消除涂膜橘皮、缩孔等表面缺陷。
- 使用于需再涂体系, 请先试验可行性。

### 使用方法

- 任何阶段添加均可。
- 使用前请预先试用所需的最低添加量。
- 为操作方便, 最好先稀释 10 - 100 倍后再使用。
- 气温低时外观可能出现混浊或凝胶现象, 温度上升即回复正常无损效用。在混浊时请搅拌均匀使用。

### 添加量

添加量视体系及需求而定。一般为对全量 0.01 - 0.2%。

### 操作与安全

小心操作, 避免接触皮肤与眼睛, 其它资料请参考物质安全资料表。

### 储存条件

- 远离热及火源。
- 置于阴凉通风处, 容器保持紧密。
- 储存环境为 0°C 至 40°C。

### 包装

净重: 200 kg / 25 kg

### 有效期

Levaslip 468 自生产日起, 保质期限为 30 个月。

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

[www.elementis-specialties-asia.com](http://www.elementis-specialties-asia.com)

B01 Nov-09

# 品质保证

本公司自 1992 年起获得 ISO 9001／9002 质量体系认证，确保所有操作符合标准规定。

## 海名斯特殊化学，亚洲

### Head Office

上海市松江工业区联阳路 99 号  
邮编 201613  
99, Lianyang Road, Songjiang  
Industrial Zone, Shanghai,  
China 201613  
Tel.: +86 21 57740348  
Fax.: +86 21 57743563

### Taiwan

新竹县湖口乡新竹工业区光复北路  
92 号  
92, Kuang-Fu North Road, Hsinchu  
Industrial Park, Hukou,  
Hsinchu, Taiwan  
Tel.: +886 3 5984035  
Fax.: +886 3 5983301

### Malaysia

Lot PT 55, 64 & 65,  
Jalan Hulu Tinggi 26/6, Seksyen 26,  
40400 Shah Alam Selangor Darul  
Ehsan, Malaysia  
Tel.: +603 5191 9979  
Fax.: +603 5191 6811

### Japan

15-14 Minamimiseba 1-Chome  
Chou-Ku, Osaka  
542-0081 Japan  
Tel.: +81 6 6267 6210  
Fax.: +81 6 6267 6213