

流平剂

产品介绍

Levaslip 810 为改性聚硅氧烷，可用于水性、溶剂型、无溶剂型涂料及油墨体系，以增加流平和平滑性。

产品特征

组成	改性聚硅氧烷
外观	澄清液体
不挥发份	≥ 90%
比重	0.99 - 1.03
粘度	1400 - 3000 cP (25°C)

应用领域

- 双组份聚氨酯涂料
- 硝基漆
- 酸固化涂料
- 紫外光固化体系

主要特性

- 增进涂膜的平滑与抗划伤，尤其在低用量下，仍有优异效果。
- 在大部分体系中有良好的相容性。
- 增进涂膜流动、流平性。
- 消除表面橘皮、缩孔等缺陷。
- 改善展色系的润湿性。
- 防止调色体系或低光泽涂膜产生贝纳尔德窝。
- 使用于需再涂体系，请先试验可行性。
- 可溶解于醇类、酯类、酮类、碳氢溶剂，部份溶于水。

使用方法

请先试验最适添加量；为操作方便，最好先稀释 5 - 10 倍后再使用，任何阶段添加均可。

添加量

对全量 0.01 - 0.2%。

操作与安全

避免接触皮肤和眼睛，其它资料请参考物质安全资料表。

储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 0°C 至 40°C。
- 低于 15°C 时，外观可能混浊或凝固，请水浴加热至室温搅拌均匀后再使用。

包装

净重：200 kg / 25 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B01 Dec-09

有效期

Levaslip 810 自生产日起，保质期限为 18 个月。

品质保证

本公司自 1992 年起获得 ISO 9001／9002 质量体系认证，确保所有操作符合标准规定。

海名斯特殊化学，亚洲

Head Office

上海市松江工业区联阳路 99 号
邮编 201613
99, Lianyang Road, Songjiang
Industrial Zone, Shanghai,
China 201613
Tel.: +86 21 57740348
Fax.: +86 21 57743563

Taiwan

新竹县湖口乡新竹工业区光复北路
92 号
92, Kuang-Fu North Road, Hsinchu
Industrial Park, Hukou,
Hsinchu, Taiwan
Tel.: +886 3 5984035
Fax.: +886 3 5983301

Malaysia

Lot PT 55, 64 & 65,
Jalan Hulu Tinggi 26/6, Seksyen 26,
40400 Shah Alam Selangor Darul
Ehsan, Malaysia
Tel.: +603 5191 9979
Fax.: +603 5191 6811

Japan

15-14 Minamimiseba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6210
Fax.: +81 6 6267 6213