

流平剂

产品介绍

Levaslip 876 为一改性的聚硅氧烷，相容性佳、底材润湿性佳，适用于大多数工业涂料，是最被广泛使用的流平剂。

产品特征

组成	改性聚硅氧烷
外观	无色至微黄色澄清液体
不挥发份	12.0 - 14.0%
溶剂	二甲苯／乙二醇苯醚
比重	约 0.93
折射率	1.49 - 1.50 (25°C)

应用领域

溶剂型涂料体系

主要特性

- 对底材的润湿性极佳，可消除因润湿不足引起涂膜皱缩、火山口等，增进涂膜流平。
- 降低涂膜摩擦系数，改善抗划伤性和增加抗粘性。
- 相容性佳，适合于大多数溶剂型涂料。
- 使用于需再涂体系，请先试验可行性。

使用方法

- 请于添加前测试最佳添加量。可在任何阶段添加，请先稀释后搅拌加入。
- 高于 35°C 可能造成外观微浊，对品质不会造成影响，可直接使用。

添加量

对全量 0.2 - 0.5%。

操作与安全

本产品含有溶剂，需小心操作，避免接触皮肤与眼睛。其它资料请参考物质安全资料表。

储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 0°C 至 35°C。

包装

净重：180 kg／25 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B01 Dec-09

有效期

Levaslip 876 自生产日起，保质期限为 18 个月。

品质保证

本公司自 1992 年起获得 ISO 9001／9002 质量体系认证，确保所有操作符合标准规定。

海名斯特殊化学，亚洲

Head Office

上海市松江工业区联阳路 99 号
邮编 201613
99, Lianyang Road, Songjiang
Industrial Zone, Shanghai,
China 201613
Tel.: +86 21 57740348
Fax.: +86 21 57743563

Taiwan

新竹县湖口乡新竹工业区光复北路
92 号
92, Kuang-Fu North Road, Hsinchu
Industrial Park, Hukou,
Hsinchu, Taiwan
Tel.: +886 3 5984035
Fax.: +886 3 5983301

Malaysia

Lot PT 55, 64 & 65,
Jalan Hulu Tinggi 26/6, Seksyen 26,
40400 Shah Alam Selangor Darul
Ehsan, Malaysia
Tel.: +603 5191 9979
Fax.: +603 5191 6811

Japan

15-14 Minamimiseba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6210
Fax.: +81 6 6267 6213