

流平剂

产品介绍

Levaslip 879 为一改性聚硅氧烷流平剂，具有极佳的触感，可增进涂膜表面滑爽。

产品特征

组成	改性聚硅氧烷
外观	无色至微黄色澄清粘稠液体
不挥发份	>95%
比重	1.02 - 1.03
折射率	1.445 - 1.449 (25°C)

应用领域

- 溶剂型涂料
 - 双组份聚氨酯涂料
 - 硝基漆
 - 丙烯酸喷漆
- 水性涂料

主要特性

- 良好的底材湿润性。
- 涂膜触感佳。
- 良好的相容性与再涂性。
- 可降低摩擦系数，提高抗划伤性。
- 使用于需再涂体系，请先试验可行性。

使用方法

- 请于添加前测试最佳添加量，以获得最佳效果，并请稀释后搅拌加入。
- 低于 5°C 会造成产品结冻，回复至室温可恢复原外观，并不影响产品品质。

添加量

对全量 0.1 - 0.5%。

操作与安全

避免接触皮肤和眼睛，其它资料请参考物质安全资料表。

储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 0°C 至 40°C。

包装

净重：25 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B01 Dec-09

有效期

Levaslip 879 自生产日起，保质期限为 18 个月。

品质保证

本公司自 1992 年起获得 ISO 9001／9002 质量体系认证，确保所有操作符合标准规定。

海名斯特殊化学，亚洲

Head Office

上海市松江工业区联阳路 99 号
邮编 201613
99, Lianyang Road, Songjiang
Industrial Zone, Shanghai,
China 201613
Tel.: +86 21 57740348
Fax.: +86 21 57743563

Taiwan

新竹县湖口乡新竹工业区光复北路
92 号
92, Kuang-Fu North Road, Hsinchu
Industrial Park, Hukou,
Hsinchu, Taiwan
Tel.: +886 3 5984035
Fax.: +886 3 5983301

Malaysia

Lot PT 55, 64 & 65,
Jalan Hulu Tinggi 26/6, Seksyen 26,
40400 Shah Alam Selangor Darul
Ehsan, Malaysia
Tel.: +603 5191 9979
Fax.: +603 5191 6811

Japan

15-14 Minamimiseba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6210
Fax.: +81 6 6267 6213