

流平剂

产品介绍

Levaslip 882 为一改性聚硅氧烷的流平剂，具有帮助消光粉排列的特性。不论粉量高低都具有良好的消光粉定位效果，并有优异的湿润性。

产品特征

组成	改性聚硅氧烷
外观	微黄色澄清至微浊液体
不挥发份	48 - 52%
溶剂	芳香族碳氢溶剂／丁内酯
比重	0.99 - 1.04
折射率	1.445 - 1.465 (25°C)

应用领域

- 硝基漆
- 双组份聚氨酯涂料

主要特性

- 针对涂料做流动控制，可于消光漆中增加消光粉定向效果，不会对光泽产生影响。
- 可降低磨擦系数，并提高抗划伤性。
- 可降低表面张力，促进底材的湿润性，避免橘皮现象发生。
- 适用于大多数消光粉涂料体系，具有极佳的相容性与再涂性。

使用方法

请于添加前测试最佳添加量，以获得最佳效果，并请稀释后搅拌加入。

添加量

对全量 0.1 - 1.0%。

操作与安全

本产品含有溶剂，需小心操作，避免接触皮肤与眼睛，其它资料请参考物质安全资料表。

储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 0°C 至 40°C。
- 低于 5°C 会造成产品分层与混浊，请回复至室温并混和均匀后使用，对品质不会造成影响。

包装

净重：25 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B01 Dec-09

有效期

Levaslip 882 自生产日起，保质期限为 18 个月。

品质保证

本公司自 1992 年起获得 ISO 9001／9002 质量体系认证，确保所有操作符合标准规定。

海名斯特殊化学，亚洲

Head Office

上海市松江工业区联阳路 99 号
邮编 201613
99, Lianyang Road, Songjiang
Industrial Zone, Shanghai,
China 201613
Tel.: +86 21 57740348
Fax.: +86 21 57743563

Taiwan

新竹县湖口乡新竹工业区光复北路
92 号
92, Kuang-Fu North Road, Hsinchu
Industrial Park, Hukou,
Hsinchu, Taiwan
Tel.: +886 3 5984035
Fax.: +886 3 5983301

Malaysia

Lot PT 55, 64 & 65,
Jalan Hulu Tinggi 26/6, Seksyen 26,
40400 Shah Alam Selangor Darul
Ehsan, Malaysia
Tel.: +603 5191 9979
Fax.: +603 5191 6811

Japan

15-14 Minamimiseba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6210
Fax.: +81 6 6267 6213