

流平剂

产品介绍

Levelol 837 为氟改性聚丙烯酸酯可再涂流平剂，提供优异流平性与底材润湿性。

产品特征

组成	氟改性聚丙烯酸酯共聚物
外观	澄清至微浊液体
不挥发份	69.0 - 72.0%
溶剂	二甲苯
比重	约 0.98
折射率	1.475 - 1.479 (25°C)

应用领域

溶剂型涂料

主要特性

- 为氟改性高分子型流平剂，具有优良的流平性及再涂性。
- 增进底材润湿及防止涂膜的缩孔、针孔、鱼眼等缺陷的产生，并获得最佳的流平性。
- 性质稳定不易水解，具有优异的耐光性与抗老化性，而且不挥发，因此于涂料体系除可增进流平外，也具有增塑效果。
- 与多数涂料体系相容性佳。

使用方法

使用前请先测试出最适当用量及涂料体系的相容性。

添加量

添加量视涂料体系而定，一般对全量 0.1 - 0.5%。

操作与安全

本产品含有溶剂，需小心操作，避免接触皮肤与眼睛。其它资料请参考物质安全资料表。

储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 0°C 至 40°C。

包装

净重：200 kg / 25 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B01 Dec-09

有效期

Levelol 837 自生产日起，保质期限为 18 个月。

品质保证

本公司自 1992 年起获得 ISO 9001／9002 质量体系认证，确保所有操作符合标准规定。

海名斯特殊化学，亚洲

Head Office

上海市松江工业区联阳路 99 号
邮编 201613
99, Lianyang Road, Songjiang
Industrial Zone, Shanghai,
China 201613
Tel.: +86 21 57740348
Fax.: +86 21 57743563

Taiwan

新竹县湖口乡新竹工业区光复北路
92 号
92, Kuang-Fu North Road, Hsinchu
Industrial Park, Hukou,
Hsinchu, Taiwan
Tel.: +886 3 5984035
Fax.: +886 3 5983301

Malaysia

Lot PT 55, 64 & 65,
Jalan Hulu Tinggi 26/6, Seksyen 26,
40400 Shah Alam Selangor Darul
Ehsan, Malaysia
Tel.: +603 5191 9979
Fax.: +603 5191 6811

Japan

15-14 Minamisisemba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6210
Fax.: +81 6 6267 6213