

流平剂

产品介绍

Levelol TSP 由高沸点化合物与特殊界面活性剂所组成，可增进涂膜的流平与防止气泡、针孔的产生，适用于各种气干、烘干型的涂料。

产品特征

组成	高沸点溶剂含界面活性剂
外观	澄清液体
有效成份	100%
溶剂	芳香族碳氢溶剂
比重	约 0.94
折射率	1.505 - 1.515 (25°C)

应用领域

溶剂型涂料

主要特性

- 为一高沸点溶剂与特殊界面活性剂所组成，对涂料、油墨的溶剂挥发与表面流动性质的改进有极佳的效果，同时可预防高湿度时所产生的发白等缺陷。
- 可控制涂膜表面溶剂挥发的速率，改善涂膜的流动性，消除橘皮、针孔、火山口等，形成非常流平与极高光泽的涂面。
- 对木材等多孔性底材有良好的渗透性，与消泡剂并用，能彻底消除因底材导管、孔洞等残留气泡所引起的细泡。
- 可缩短烘漆喷涂后的静置时间，消除湿膜遇到瞬间高热所产生的起泡困扰。
- 添加于浸渍、喷涂的涂料中可防止喷溅造成的凹痕与相接面的界迹，对边缘增厚的现象亦可化解。
- 用在丝网油墨可使丝网易于自印模脱离，而不留下网迹或造成气泡。

使用方法

添加量视涂料体系而异。

添加量

一般对全溶剂量的 5 - 10% 或对全量的 2 - 5%。

操作与安全

本产品有溶剂，需小心操作，避免接触皮肤和眼睛。其它资料请参考物质安全资料表。

储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 0°C 至 40°C。

包装

净重：180 kg / 25 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B01 Nov-09

有效期

Levelol TSP 自生产日起，保质期限为 18 个月。

品质保证

本公司自 1992 年起获得 ISO 9001／9002 质量体系认证，确保所有操作符合标准规定。

海名斯特殊化学，亚洲

Head Office 上海市松江工业区联阳路 99 号 邮编 201613 99, Lianyang Road, Songjiang Industrial Zone, Shanghai, China 201613 Tel.: +86 21 57740348 Fax.: +86 21 57743563	Taiwan 新竹县湖口乡新竹工业区光复北路 92 号 92, Kuang-Fu North Road, Hsinchu Industrial Park, Hukou, Hsinchu, Taiwan Tel.: +886 3 5984035 Fax.: +886 3 5983301	Malaysia Lot PT 55, 64 & 65, Jalan Hulu Tinggi 26/6, Seksyen 26, 40400 Shah Alam Selangor Darul Ehsan, Malaysia Tel.: +603 5191 9979 Fax.: +603 5191 6811	Japan 15-14 Minamimisemba 1-Chome Chou-Ku, Osaka 542-0081 Japan Tel.: +81 6 6267 6210 Fax.: +81 6 6267 6213
---	--	--	---