

润湿分散剂

产品介绍

Disponer 926 为一适用于各种溶剂型涂料和油墨的优异润湿分散剂，尤其针对各种高级颜料，如碳黑、菁蓝等具有良好的分散效果，而能得到更佳的展色性。

产品特征

组成	阴离子性表面活性剂
外观	微黄色粘稠液体
不挥发份	82 - 88 %
比重	约 1.04
折射率	1.457 - 1.467 (25°C)

应用领域

- 调和漆
- 环氧涂料
- 氯化橡胶

主要特性

- 对于碳黑、酞菁蓝等高级颜料的分散及展色性能优异，不仅缩短研磨时间，更能获得最佳的鲜艳度与着色力，同时能延缓成品漆颜料凝聚及粘度上升的情形。
- 用于般颜料（如钛白粉）的分散时，因其具有强吸附力的官能基与颜料吸附，并溶合于树脂液中，形成颜料—分散剂—树脂的稳定状态，提供了良好的分散安定性、流动性并预防浮色、发花的发生。
- 亦极适合应用于各种油墨体系，不仅能缩短研磨分散时间、降低研磨份粘度，提高操作性，同时能增进油墨的光泽、展色强度。

使用方法

- 研磨前添加。
- 若添加过量会因游离分散剂太多，而影响涂膜硬度或分散剂被金属底材吸附而影响涂膜附着性。

添加量

- 对有机颜料量 1.0 - 3.0%
- 对无机颜料量 0.5 - 1.5%。

操作与安全

使用本产品时，须小心操作，避免接触皮肤与眼睛，其它资料请参考物质安全资料表。

储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 5°C 至 40°C。
- 低于 5°C 时外观可能结冻或混浊状，请隔水加热至澄清状态再搅拌均匀方可使用。

包装

净重：200 kg / 25 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B01 Nov-09

有效期

Disponer 926 自生产日起，保质期限为 18 个月。

品质保证

本公司自 1992 年起获得 ISO 9001/9002 质量体系认证，确保所有操作符合标准规定。

海名斯特殊化学，亚洲

Head Office

上海市松江工业区联阳路 99 号
邮编 201613
99, Lianyang Road, Songjiang
Industrial Zone, Shanghai,
China 201613
Tel.: +86 21 57740348
Fax.: +86 21 57743563

Taiwan

新竹县湖口乡新竹工业区光复北路
92 号
92, Kuang-Fu North Road, Hsinchu
Industrial Park, Hukou,
Hsinchu, Taiwan
Tel.: +886 3 5984035
Fax.: +886 3 5983301

Malaysia

Lot PT 55, 64 & 65,
Jalan Hulu Tinggi 26/6, Seksyen 26,
40400 Shah Alam Selangor Darul
Ehsan, Malaysia
Tel.: +603 5191 9979
Fax.: +603 5191 6811

Japan

15-14 Minaminisemba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6210
Fax.: +81 6 6267 6213