

紫外光固化低聚物

产品介绍

Hypomer VP-UR-801 是设计用于塑料涂装的聚氨酯丙烯酸酯。Hypomer VP-UR-801 特别适用于真空镀紫外光底漆。

产品特征

组成	聚氨酯丙烯酸酯
外观	微黄色粘稠液体
色度	<150 APHA
不挥发份	79 - 83%
溶剂	乙酸正丁酯
折射率	1.478-1.482
粘度	14000 - 24000 cP (25°C)
比重	约 1.1

应用领域

- 紫外光固化涂料与油墨
- 塑料涂料

主要特性

- 与铝蒸气有良好附着性
- 兼具硬度与可挠性
- 固化速度快

使用方法

当作涂料中的主体树脂，搭配稀释单体，光起始剂，与溶剂配成涂料。

添加量

建议对涂料固成份 40 - 60%。

操作与安全

本产品含有溶剂，须小心操作，避免接触皮肤与眼睛，其他资料请参考物质安全资料表。

储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 0°C 至 40°C。

包装

净重：200 kg

有效期

Hypomer VP-UR-801 生产日起，保质期限为 12 个月。

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2009, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B02 Nov-09

品质保证

本公司自 1992 年起获得 ISO 9001／9002 质量体系认证，确保所有操作符合标准规定。

Elementis Specialties, Asia

Head Office

99, Lianyang Road, Songjiang
Industrial Zone, Shanghai,
China 201613
Tel.: +86 21 57740348
Fax.: +86 21 57743563

Taiwan

92, Kuang-Fu North Road, Hsinchu
Industrial Park, Hukou,
Hsinchu, Taiwan
Tel.: +886 3 5984035
Fax.: +886 3 5983301

Malaysia

Lot PT 55, 64 & 65,
Jalan Hulu Tinggi 26/6, Seksyen 26,
40400 Shah Alam Selangor Darul
Ehsan, Malaysia
Tel.: +603 5191 9979
Fax.: +603 5191 6811

Japan

15-14 Minamimisemba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6210
Fax.: +81 6 6267 6213