

附着增进剂

产品介绍

Adherent CP-7540 为氯化聚烯烃改性丙烯酸树脂，广泛应用于 PP 底材作为附着底涂，用以增进涂料对 PP 底材附着性。

产品特征

组成	氯化聚烯烃改性丙烯酸树脂
外观	混浊液体
不挥发份	44.5 - 47.5%
溶剂	甲苯
比重	约 0.95
粘度	1500 - 3000 cP (25°C)
酸价	1 - 4 mg KOH/g (100%)
折射率	1.494 - 1.496 (25°C)

应用领域

- PP 或 PP/EPDM 底漆
- 为汽车内装用一次涂装的一液型面漆
- 一般丙烯酸或聚氨酯涂料的底漆

主要特性

- 广泛应用于塑料上的涂料体系。
- 为附着底漆的涂膜，经上涂后可得优异的附着性、耐水性。
- 增进对 PP 底材的附着性

使用方法

- 加入颜料直接研磨作成底色漆。
- 直接或与树脂作成底色漆，使用前请试验最适添加量。

添加量

决定于涂料体系，使用前请试验最适添加量。

操作与安全

- Adherent CP-7540 可能因为溶剂挥发或低温导致粘度上升，甚至凝胶。
- 一旦发生凝胶，可采用水浴加热到 50 - 60 °C，必要时可补充一些甲苯，如此即可恢复流动性而且不影响性能。
- 本产品含有溶剂，须小心操作，避免接触皮肤与眼睛，其他资料请参考物质安全资料表。

储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 0°C 至 40°C。

包装

净重：190 kg / 25 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B01 Nov-09

有效期

Adherent CP-7540 自生产日起，保质期限为 12 个月。

品质保证

本公司自 1992 年起获得 ISO 9001／9002 质量体系认证，确保所有操作符合标准规定。

海名斯特殊化学，亚洲

Head Office 上海市松江工业区联阳路 99 号 邮编 201613 99, Lianyang Road, Songjiang Industrial Zone, Shanghai, China 201613 Tel.: +86 21 57740348 Fax.: +86 21 57743563	Taiwan 新竹县湖口乡新竹工业区光复北路 92 号 92, Kuang-Fu North Road, Hsinchu Industrial Park, Hukou, Hsinchu, Taiwan Tel.: +886 3 5984035 Fax.: +886 3 5983301	Malaysia Lot PT 55, 64 & 65, Jalan Hulu Tinggi 26/6, Seksyen 26, 40400 Shah Alam Selangor Darul Ehsan, Malaysia Tel.: +603 5191 9979 Fax.: +603 5191 6811	Japan 15-14 Minamisisemba 1-Chome Chou-Ku, Osaka 542-0081 Japan Tel.: +81 6 6267 6210 Fax.: +81 6 6267 6213
---	--	--	---