

润湿分散剂

产品介绍

Disponer 9850 适用于溶剂型的涂料体系，有良好的润湿分散效果，对不易分散的有机颜料效果佳。

产品特征

组成	聚氨酯化合物
外观	无色至微黄色液体
不挥发份	44 - 47%
溶剂	二甲苯 / 丙二醇单甲醚乙酸酯 / 乙酸正丁酯
比重	0.96 - 1.00
折射率	1.472 - 1.476 (25°C)

应用领域

- 适用于大多数的有机颜料
- 适用于低至中极性体系：
 - 醇酸 / 胺基树脂
 - 丙烯酸 / 胺基树脂
 - 丙烯酸聚氨酯涂料

主要特性

- 具有立体障碍结构、极佳的分散能力，可缩短颜料分散时间。
- 可提供涂膜优异的清晰度、光泽度、展色性及遮蔽力。
- 具有良好的分散及防颜料絮凝效果。

使用方法

研磨前添加

添加量

- 对有机颜料添加 40 - 120%。
- 由于颜料的表面特性及吸油量不尽相同，而且分散剂在各种涂料体系中的相容性亦可能有所变化，建议客户作一系列对颜料不同添加量的试验，以获得最佳效果。

操作与安全

本产品含有溶剂，需小心操作，避免接触皮肤与眼睛，其它资料请参考物质安全资料表。

储存条件

- 远离热火星及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 0°C 至 40°C。
- 低于 8°C 时外观可能混浊或分离，请加热到澄清状态，搅拌均匀后使用。
- 容器打开后，未使用完毕需完全密封，防止水气进入。

包装

净重：180 kg / 25 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B01 Nov-09

有效期

Disponer 9850 自生产日起，保质期限为 18 个月。

品质保证

本公司自 1992 年起获得 ISO 9001/9002 质量体系认证，确保所有操作符合标准规定。

海名斯特殊化学，亚洲

Head Office

上海市松江工业区联阳路 99 号
邮编 201613
99, Lianyang Road, Songjiang
Industrial Zone, Shanghai,
China 201613
Tel.: +86 21 57740348
Fax.: +86 21 57743563

Taiwan

新竹县湖口乡新竹工业区光复北路
92 号
92, Kuang-Fu North Road, Hsinchu
Industrial Park, Hukou,
Hsinchu, Taiwan
Tel.: +886 3 5984035
Fax.: +886 3 5983301

Malaysia

Lot PT 55, 64 & 65,
Jalan Hulu Tinggi 26/6, Seksyen 26,
40400 Shah Alam Selangor Darul
Ehsan, Malaysia
Tel.: +603 5191 9979
Fax.: +603 5191 6811

Japan

15-14 Minaminisemba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6210
Fax.: +81 6 6267 6213