

流变助剂

产品介绍

DeuRheo 2810 为液状流变助剂, 适用于溶剂型涂料体系, 使用方便不需调整体系的活化温度。

产品特征

组成	改性聚脲化合物
外观	黄棕色液体
不挥发份	50 - 54%
溶剂	N-甲基吡咯酮
比重	约 1.11
粘度	200 - 600 cP (25°C)
折射率	1.51 - 1.52 (25°C)

应用领域

- 溶剂型环氧涂料
- 聚氨酯涂料
- 丙烯酸涂料

主要特性

- 在涂料中建立三维结构, 赋予涂料触变性, 避免涂料流挂与颜填料沉淀。
- 维持涂料稀释后的触变性, 避免施工过程中颜料与填充料沉淀。

使用方法

- 前添加时须与颜料共同研磨, 后添加时须以高速搅拌分散均匀。
- 在溶剂体系中添加适量的醇类溶剂有助于 DeuRheo 2810 的分散。

添加量

- 防沉降: 对全量 0.1 - 0.3%。
- 防流挂: 对全量 0.5 - 1.0%

操作与安全

本产品含有溶剂, 须小心操作, 避免接触皮肤与眼睛, 其它资料请参考物质安全资料表。

储存条件

- 远离热及火源。
- 置于阴凉通风处, 容器保持紧密。
- 储存环境为 0°C 至 40°C。
- 低于 5°C 时, 外观可能结冻, 请隔水加热至液状后, 搅拌均匀后使用。
- 容器打开后未使用完毕需密封完全防止水气进入。

包装

净重: 25 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B01 Nov-09

有效期

DeuRheo 2810 自生产日起，保质期限为 12 个月。

品质保证

本公司自 1992 年起获得 ISO 9001／9002 质量体系认证，确保所有操作符合标准规定。

海名斯特殊化学，亚洲

Head Office

上海市松江工业区联阳路 99 号
邮编 201613
99, Lianyang Road, Songjiang
Industrial Zone, Shanghai,
China 201613
Tel.: +86 21 57740348
Fax.: +86 21 57743563

Taiwan

新竹县湖口乡新竹工业区光复北路
92 号
92, Kuang-Fu North Road, Hsinchu
Industrial Park, Hukou,
Hsinchu, Taiwan
Tel.: +886 3 5984035
Fax.: +886 3 5983301

Malaysia

Lot PT 55, 64 & 65,
Jalan Hulu Tinggi 26/6, Seksyen 26,
40400 Shah Alam Selangor Darul
Ehsan, Malaysia
Tel.: +603 5191 9979
Fax.: +603 5191 6811

Japan

15-14 Minamimisemba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6210
Fax.: +81 6 6267 6213