

Irgalite® Yellow GO

Colour Index	Pigment Yellow 74 11741
chemical nature	arylamide
physical form	powder



fig. 1	fig. 2	fig. 3
alkyd/melamine full shade	air-drying soya alkyd 1/3 standard depth of shade	air-drying soya alkyd 1/25 standard depth of shade

fastness to weathering	alkyd/ melamine system
full shade	4–5
1/25 standard depth of shade	4

fastness to light	alkyd/ melamine system
full shade	7–8
1/25 standard depth of shade	7

suitability for industries					
automotive	general industrial	coil	powder	wood	decorative
<input type="radio"/>	<input checked="" type="radio"/>	<input type="radio"/>	<input type="radio"/>	<input type="radio"/>	<input checked="" type="radio"/>

suitability for applications					
baking finishes	water-based	acrylic/isocyanate	acid-curable	amine-curable	air-drying
<input checked="" type="radio"/>	<input checked="" type="radio"/>	<input type="radio"/>	<input type="radio"/>	<input type="radio"/>	<input checked="" type="radio"/>

explanation of symbols	<input checked="" type="radio"/> suitable	<input checked="" type="radio"/> potentially suitable	<input type="radio"/> not suitable
-------------------------------	---	---	------------------------------------

physical data			
density	bulk volume	specific surface	oil absorption
1.30 g/cm ³	3.2 l/kg	20 m ² /g	37 g/100 g

thermal resistance	
150 °C (302 °F) / 30 min.	200 °C (392 °F) / 10 min.
5	3

fastness to overcoating

baking finish, 130 °C (266°F) / 30 min.

2–3

resistance to solvents**butyl acetate**

2–3

ethanol

3–4

methylethyl ketone

2–3

water

5

white spirit

4

xylene

2–3

resistance to chemicals**acid**

5

alkali

5

Please contact your BASF sales representative for more information on the test methods applied.

The proximity of the demonstrated shades to the original hues depends on the settings and calibration of the equipment used (monitor, printer).

Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

It cannot be ruled out that this product contains particles < 0.1 µm.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of the BASF Group, unless otherwise noted

BASF SE
Pigments & Resins Europe
67056 Ludwigshafen, Germany
www.basf.com/pigment
service-edc@basf.com