

水性消泡剂

产品介绍

DAPRO® DF 7035 为一不含有机硅、经济且通用的水性消泡剂。

产品特征

外观	淡琥珀色蜡状液体
活性分	65%
密度	870 kg/m ³ (25°C) (ISO 2811-2)
粘度	1000 – 4000 mPa.s (25°C) (ASTM D 2196)
溶解性	水中乳化性弱
组成	矿物油与蜡的混合物，不含有机硅

应用领域

- 乳胶漆
- 其他对表面缺陷敏感的水性体系

主要特性

DAPRO® DF 7035 基于矿物油和蜡，并含有少量特殊有机酯。特别推荐用于对表面缺陷敏感的体系。采用特殊的制备工艺，具有非常好的产品储存稳定性。

特点	益处
水中乳化性低	提供长期消泡效果 降低对水分的敏感，增加耐擦洗性
经济性	减低成本
不含有机硅	表面缺陷产生和附着力丧失的可能性降到最低 应用范围广

使用方法

至少加入 DAPRO® DF 7035 总量的一半到研磨浆料部分，余下的部分在调漆阶段添加。

添加量

DAPRO® DF 7035 准确的添加量应视具体情况而定。一般为对配方总量的 0.3 - 0.8% 就可获得理想的效果。

操作与安全

每种产品均有操作与安全性方面的详细资料。在使用该产品前请参阅相关的物质安全资料表 (MSDS)。

储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境温度为 4°C (40°F) 以上。

包装

DAPRO® DF 7035 可提供桶装与散装形式。请与您所在当地海名斯特殊化学的代表联系，选用适合当地的具体包装形式和包装重量。

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B01 Dec-09

有效期

DAPRO® 7035 自生产日起, 保质期限为 12 个月。

品质保证

本公司自 1992 年起获得 ISO 9001／9002 质量体系认证，确保所有操作符合标准规定。

海名斯特殊化学，亚洲

Head Office 上海市松江工业区联阳路 99 号 邮编 201613 99, Lianyang Road, Songjiang Industrial Zone, Shanghai, China 201613 Tel.: +86 21 57740348 Fax.: +86 21 57743563	Taiwan 新竹县湖口乡新竹工业区光复北路 92 号 92, Kuang-Fu North Road, Hsinchu Industrial Park, Hukou, Hsinchu, Taiwan Tel.: +886 3 5984035 Fax.: +886 3 5983301	Malaysia Lot PT 55, 64 & 65, Jalan Hulu Tinggi 26/6, Seksyen 26, 40400 Shah Alam Selangor Darul Ehsan, Malaysia Tel.: +603 5191 9979 Fax.: +603 5191 6811	Japan 15-14 Minaminisemba 1-Chome Chou-Ku, Osaka 542-0081 Japan Tel.: +81 6 6267 6210 Fax.: +81 6 6267 6213
---	--	--	---