

## 水性消泡剂

### 产品介绍

Defom W-052 是以改性聚硅氧烷为主要成分的消泡剂。特别设计用于高粘度厚浆漆体系的抑泡、消泡。

### 产品特征

组成	改性聚硅氧烷乳液
外观	乳白色液体
不挥发份	49 - 52%
溶剂	水
比重	约 1.0

### 应用领域

- 具有优异的抑泡、消泡效果，且具长效性。
- 施工过程中能快速破泡、消泡比较彻底、不留残泡。
- 如有缩孔现象发生请降低添加量，此时可搭配相容性佳的消泡剂使用，即可获得最佳的抑泡、消泡效果，也不会造成涂膜缺陷。
- 在较大范围的 pH 值、温度及剪切力下具有优异的稳定性，对光泽影响小。
- 可分散于水中

### 主要特性

高粘度厚浆体系，如弹性拉毛乳胶漆体系。

### 使用方法

- 在生产的前后阶段加入均可，但应充分分散均匀。
- 可以原液形式直接添加。如需稀释使用，以水稀释即可。

### 添加量

添加量视体系及需求而定。一般为对全量 0.1 - 1.0%。

### 操作与安全

操作时避免接触皮肤和眼睛，其它资料请参考物质安全资料表。

### 储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 5°C 至 40°C。
- 低于 0°C 可能会冻结，需置于 25°C 环境下融化，并搅匀后使用。
- 储存长时间后可能有分层现象产生，应搅拌均匀后取用。

### 包装

净重：200 kg / 25 kg

*NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.*

*© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.*

*® Trademark of Elementis Specialties, Inc.*

[www.elementis-specialties-asia.com](http://www.elementis-specialties-asia.com)

B01 Apr-09

## 有效期

Defom W-052 自生产日起，保质期限为 18 个月。

## 品质保证

本公司自 1992 年起获得 ISO 9001/9002 质量体系认证，确保所有操作符合标准规定。

---

### 海名斯特殊化学，亚洲

#### Head Office

上海市松江工业区联阳路 99 号  
邮编 201613  
99, Lianyang Road, Songjiang  
Industrial Zone, Shanghai,  
China 201613  
Tel.: +86 21 57740348  
Fax.: +86 21 57743563

#### Taiwan

新竹县湖口乡新竹工业区光复北路  
92 号  
92, Kuang-Fu North Road, Hsinchu  
Industrial Park, Hukou,  
Hsinchu, Taiwan  
Tel.: +886 3 5984035  
Fax.: +886 3 5983301

#### Malaysia

Lot PT 55, 64 & 65,  
Jalan Hulu Tinggi 26/6, Seksyen 26,  
40400 Shah Alam Selangor Darul  
Ehsan, Malaysia  
Tel.: +603 5191 9979  
Fax.: +603 5191 6811

#### Japan

15-14 Minaminisemba 1-Chome  
Chou-Ku, Osaka  
542-0081 Japan  
Tel.: +81 6 6267 6210  
Fax.: +81 6 6267 6213