

紫外光固化低聚物

产品介绍

Hypomer UR-61 为高官能度紫外光树脂，提供涂料硬度与耐磨性能。

产品特征

组成	脂肪族丙烯酸酯低聚物
外观	澄清至微浊粘稠液体
色度	≤ 100 APHA
有效成份	100%
比重	约 1.10
粘度	30000 - 60000 cP (25°C)
折射率	1.492 - 1.496 (25°C)

应用领域

- 紫外光固化涂料及油墨
- 铝粉漆金油
- 木器涂料
- 塑料涂料

主要特性

- 高固化速度
- 硬度与耐磨性佳

使用方法

当作涂料中的添加树脂，搭配其他树脂，稀释单体，光起始剂与溶剂配成涂料。

添加量

建议对涂料固成份 10 - 50%。

操作与安全

小心操作，避免接触皮肤与眼睛，其他资料请参考物质安全资料表。

储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 0°C 至 40°C。

包装

净重：200 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B02 Feb-10

有效期

Hypomer UR-61 自生产日起，保质期限为 12 个月。

品质保证

本公司自 1992 年起获得 ISO 9001／9002 质量体系认证，确保所有操作符合标准规定。

海名斯特殊化学，亚洲

Head Office

上海市松江工业区联阳路 99 号
邮编 201613
99, Lianyang Road, Songjiang
Industrial Zone, Shanghai,
China 201613
Tel.: +86 21 57740348
Fax.: +86 21 57743563

Taiwan

新竹县湖口乡新竹工业区光复北路
92 号
92, Kuang-Fu North Road, Hsinchu
Industrial Park, Hukou,
Hsinchu, Taiwan
Tel.: +886 3 5984035
Fax.: +886 3 5983301

Malaysia

Lot PT 55, 64 & 65,
Jalan Hulu Tinggi 26/6, Seksyen 26,
40400 Shah Alam Selangor Darul
Ehsan, Malaysia
Tel.: +603 5191 9979
Fax.: +603 5191 6811

Japan

15-14 Minamimiseba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6210
Fax.: +81 6 6267 6213