

附着增进剂

产品介绍

Adherent ADK 为增进复合油墨对 PET 材质附着性，以及溶剂型涂料对层间密着和各种塑料、金属底材的密着性的添加剂。

产品特征

组成	不含硅酮的高分子溶液
外观	微黄澄清至微浊液体
不挥发份	21 - 23%
溶剂	乙酸丁酯
比重	约 0.930
折射率	1.415 - 1.425 (25°C)

应用领域

- 凹版复合 PET 膜油墨／溶剂型涂料

主要特性

- 油墨体系：
 - 极少的添加量，即可增进复合油墨对 PET 材质附着性。
 - 适当的配方调整，即可扩展普通轻包装油墨的通用性。
 - 相容性佳，不影响印刷油墨的光泽及色浓度。
- 涂料体系：
 - 增进涂层之间的层间附着性。
 - 可适当提高对各种塑料、金属底材的附着性。

使用方法

在研磨分散后期，以原液方式高速搅拌添加。

添加量

添加量为对油墨全量 0.4 - 1.5%，使用前请先试验相容性。

操作与安全

- 本产品含有溶剂，须小心操作，避免接触皮肤与眼睛，其它资料请参考物质全资料表。

储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 8°C 至 40°C，若于低温长时间储存，会有变浊及絮状物产生，请先搅拌均匀后再使用。

包装

净重：25 kg

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

www.elementis-specialties-asia.com

B01 Nov-09

有效期

Adherent ADK 自生产日起，保质期限为 18 个月。

品质保证

本公司自 1992 年起获得 ISO 9001／9002 质量体系认证，确保所有操作符合标准规定。

海名斯特殊化学，亚洲

Head Office

上海市松江工业区联阳路 99 号
邮编 201613
99, Lianyang Road, Songjiang
Industrial Zone, Shanghai,
China 201613
Tel.: +86 21 57740348
Fax.: +86 21 57743563

Taiwan

新竹县湖口乡新竹工业区光复北路
92 号
92, Kuang-Fu North Road, Hsinchu
Industrial Park, Hukou,
Hsinchu, Taiwan
Tel.: +886 3 5984035
Fax.: +886 3 5983301

Malaysia

Lot PT 55, 64 & 65,
Jalan Hulu Tinggi 26/6, Seksyen 26,
40400 Shah Alam Selangor Darul
Ehsan, Malaysia
Tel.: +603 5191 9979
Fax.: +603 5191 6811

Japan

15-14 Minamimisemba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6210
Fax.: +81 6 6267 6213